

## Sexy Dolls Silicone

### ***Product Description:***

Sexy Dolls Silicone is great to make silicone sexy dolls products such as sexy dolls for man, silicone dolls for woman, silicone buttocks, silicone breast pads etc.

With platinum cured which is environmental friendly, odorless and nontoxic.

Meanwhile sexy dolls silicone have soft hardness and excellent tension and tear strength and resilience .



### ***Appearance:***

Part A: an non-toxic and odorless liquid in translucent/skin color with platinum inside

Part B: an non-toxic and odorless liquid in translucent/skin color.

**ATT:** We do any curing time as your requirements



**Features:**

- ✧ Amazing fluidity and easy to operate
- ✧ Platinum-based (environmental, odorless and nontoxic)
- ✧ Mixing ration: 1:1 for easy mixing ration
- ✧ Easy de-molding
- ✧ Excellent tension and tear strength
- ✧ High performance in duplication
- ✧ almost nil shrinkage below 0.1
- ✧ Excellent resistance to weather, temperature, aging, acid & aging-Proofing.
- ✧ High resistance to high temperature and aging(resist -60 to 250°C)

**Model Code:** R210, R215, R220

**Technical Data:**

**Notes:** The data are based on the operation under room temperature of 25 °C.

Typical general characteristics	Inspection Method	Value			
		R210	R215	R220	R225
Product data (Catalyzed A+B)					
<b>Hardness</b>	Shore A	10±2	15±2	20±2	25±2
<b>Mix Ratio</b>	A:B	1:1	1:1	1:1	1:1
<b>Color</b>	/	Translucent	Translucent	Translucent	Translucent
<b>Pot life</b>	25 °C (77F)	20-40mins	20-40mins	20-40mins	20-40mins
<b>Curing time</b>	25 °C (77F)	3- 5hrs	3- 5hrs	3- 5hrs	3- 5hrs
<b>Viscosity</b>	mPa.s	4000±1000	5000±1000	5500±1500	6000±1500
<b>Tear-Strength</b>	kN/m	≥15	≥18	≥26	≥26
<b>Tensile -Strength</b>	MPa	≥3.5	≥5.5	≥6.0	≥6.0
<b>Elongation</b>	%	≥450	≥450	≥500	≥500
<b>Shrinkage</b>	%	≤0.1	≤0.1	≤0.1	≤0.1

**Packing:**

**Part A :** 1kg, 5kg, 20kg, 25kg, 200kg, Vacuumed Packing in white color

**Part B:** 1kg, 5kg, 20kg, 25kg, 200kg, Vacuumed Packing in sky blue color



### **Storage & Shelf Life:**

1Year at least, stored in a cool and dry place under room temperature 25°C

### **Operation Method:**

Both Pouring or injection operation methods for our sexy dolls silicone are available. You can chose the best one as your preference, we can provide any viscosity as your requirement.



### **Caution - Safety First !!!**

1. Read the material safety data sheet(MSDS) before use.
2. Keep Out Of Reach Of Children.
3. Be careful. Use only with adequate ventilation. Contact with skin and eyes may cause irritation. Flush eyes with water for 15mins and seek immediate medical attention. Remove from skin with water-less hand cleaner followed by soap & water.

